

## Breather Fabrics

PET Breather/Bleeder

### Product Numbers

PV-90 and PV-92

### Description

Drapes easily and works well with single curvature and complex parts. This polyester breather fabric is good for autoclave pressure processes and can be used in multiple layers to increase the flow capacity. PRO-VAC 4.4 oz./yd<sup>2</sup> (150 gsm) Breather Fabric is 0.07 in (1.8 mm) thick and has a maximum use temperature is 400°F (204 °C). PRO-VAC 10 oz./yd<sup>2</sup> (340 gsm) Breather Fabric is 0.10 in (2.5 mm) thick and has a maximum use temperature of 400°F (204°C).



Pre-production trials are recommended to confirm suitability of PRO-VAC Vacuum Consumables with your unique laminate schedules and processes.

### Technical Data

Fabric Property	PV-90		PV-92		Test Standard
<b>Areal Weight</b>	150 g/m <sup>2</sup>	4.42 oz/yd <sup>2</sup>	340 g/m <sup>2</sup>	10 oz/yd <sup>2</sup>	ISO 9073-1
<b>Thickness</b>	1.8 mm	0.07 in.	2.5 mm	0.10 in.	ISO 9863-1
<b>Standard Roll Length</b>	100 m	328'	50 m	164'	
<b>Standard Roll Width</b>	1.52 m	5'	1.52m	5'	
<b>Composition</b>	100% PET		100% PET		
<b>Melting Point</b>	250°C	482°F	250°C	482°F	
<b>Maximum Use Temp</b>	204°C	400°F	204°C	400°F	
<b>Color</b>	White		White		

### Packaging and Storage

Store in original packaging.

